

**LCP(Liquid Crystal Polymer)**

**VECTRA®**

A130

VF2001/BK010P/BK0  
25P

(Standard grade)

## NOTES TO USERS

- All property values shown in this brochure are the typical values obtained under varying conditions prescribed by applicable standards and test method.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure. Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to the appropriate **"Technical Catalog"** for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Material Safety Data Sheet **"MSDS"** of the proper material.
- This brochure is edited based on reference literatures, information and data currently available to us. So the contents of this brochure are subject to change without notice due to new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

\* **"VECTRA®"** is a registered trademark of Polyplastics in Japan. **"Vectra®"**, **"Celcon®"**, **"Celanex®"** and **"Celanese®"** are registered trademarks of U.S. Company Ticona LLC in the U.S. and other countries.

# General Properties of A130

table1-1 General Properties (ISO)

Item	Unit	Test Method	Standard
			A130
			Glass fiber reinforced, Standard
Color			VF2001/BK010P/BK025P
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>LCP-GF30<
Density	g/cm <sup>3</sup>	ISO 1183	1.61
Water absorption (23℃,24hrs)	%	ISO 62	0.02
Tensile strength	MPa	ASTM D638	210
Tensile elongation	%	ASTM D638	2.2
Flexural strength	MPa	ISO 178	270
Flexural modulus	MPa	ISO 178	15,000
Flexural strain	%	ISO 178	3
Charpy impact strength (notched)	kJ/m <sup>2</sup>	ISO 179/1eA	35
Temperature of deflection under load (1.8MPa)	℃	ISO 75-1,2	240
Temperature of deflection under load (0.45MPa)	℃	ISO 75-1,2	-
Dielectric breakdown strength (1mmt)	kV/mm	IEC 60243-1	45
Dielectric breakdown strength (3mmt)	kV/mm	IEC 60243-1	24
Volume resistivity	Ω·cm	IEC 60093	3 × 10 <sup>16</sup>
Volume resistivity (Our standard)	Ω·cm	-	-
Dielectric constant (1kHz)		IEC 60250	4.1
Dielectric constant (1MHz)		IEC 60250	3.7
Dielectric dissipation factor (1kHz)		IEC 60250	0.02
Dielectric dissipation factor (1MHz)		IEC 60250	0.02
Tracking resistance (CTI)	V	IEC 60112	125
Arc resistance	s		137
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure 60MPa)	%	-	0.01
Mold Shrinkage (80×80×1mmt, Trans-direction, Inj. pressure60MPa)	%	-	0.45
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure79MPa)	%	-	-
Mold Shrinkage (80×80×1mmt, Trans direction, Inj pressure 79MPa)	%	-	-
Flammability		UL94	V-0

Item	Unit	Test Method	Standard
			A130
			Glass fiber reinforced, Standard
The yellow card File No.			E106764
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

**Polyplastics**

## **POLYPLASTICS CO., LTD.**

JR Shinagawa East Building  
18-1, Konan 2-chome, Minato-ku, Tokyo 108-8280 Japan  
Phone: 81-3-6711-8600

- *Affiliates*

Polyplastics Asia Pacific Sdn. Bhd.(Kuala Lumpur)  
Polyplastics Asia Pacific Singapore Pte.Ltd.(Singapore)  
Polyplastics Marketing (T) Ltd.(Bangkok)  
Polyplastics China Limited (Hong Kong)  
Polyplastics (Shanghai) Ltd.(Shanghai)  
Polyplastics Trading (Shanghai) Ltd.(Shanghai)  
Polyplastics Taiwan Co., Ltd.(Taipei)  
PTM Engineering Plastics (Nantong) Co., Ltd.(Nantong)