

Acetal Copolymer

DURACON®

GB-25R

CF3500/CD3501

(Low Warpage grade)

Polyplastics

NOTES TO USERS

- All property values shown in this brochure are the typical values obtained under varying conditions prescribed by applicable standards and test methods.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure. Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to the appropriate **"Technical Catalog"** for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Material Safety Data Sheet **"MSDS"** of the proper material.
- This brochure is edited based on reference literatures, information and data currently available to us. So the contents of this brochure are subject to change without notice due to new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

"DURACON®" is a registered trademark of Polyplastics Co., Ltd. in Japan and other countries.

General Properties of GB-25R

table1-1 General Properties (ISO)

Item	Unit	Test Method	Low Warpage
			GB-25R
			Low warpage
Color			CF3500/CD3501
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>POM-GB25<
Density	g/cm ³	ISO 1183	1.59
Tensile strength	MPa	ISO 527-1,2	59
Strain at break	%	ISO 527-1,2	10
Flexural strength	MPa	ISO 178	104
Flexural modulus	MPa	ISO 178	3,800
Charpy impact strength (notched)	kJ/m ²	ISO 179/1eA	3.4
Temperature of deflection under load (1.8MPa)	℃	ISO 75-1,2	110
Coefficient of linear thermal expansion (23～55℃、Flow direction)	x10 ⁻⁵ /℃	ISO 11359-2	9
Coefficient of linear thermal expansion (23～55℃、Transverse direction)	x10 ⁻⁵ /℃	ISO 11359-2	9
Dielectric breakdown strength (3mmt)	kV/mm	IEC 60243-1	21
Volume resistivity	Ω・cm	IEC 60093	2 × 10 ¹⁶
Surface resistivity	Ω	IEC 60093	7 × 10 ¹⁶
Flammability		UL94	HB
The yellow card File No.			E45034
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

※1) Nominal strain at break

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

Polyplastics

POLYPLASTICS CO., LTD.

JR Shinagawa East Building
18-1, Konan 2-chome, Minato-ku, Tokyo 108-8280 Japan
Phone: 81-3-6711-8600

- *Affiliates*

Polyplastics Asia Pacific Sdn. Bhd.(Kuala Lumpur)
Polyplastics Asia Pacific Singapore Pte.Ltd.(Singapore)
Polyplastics Marketing (T) Ltd.(Bangkok)
Polyplastics China Limited (Hong Kong)
Polyplastics (Shanghai) Ltd.(Shanghai)
Polyplastics Trading (Shanghai) Ltd.(Shanghai)
Polyplastics Taiwan Co., Ltd.(Taipei)
PTM Engineering Plastics (Nantong) Co., Ltd.(Nantong)