



Edgetek™ 5209 Black 30 A 1

Acetal (POM) Copolymer

Key Characteristics

Product Description

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Features	• Copolymer • General Purpose	• Good Wear Resistance • Low Friction	
Uses	• Automotive Applications • Bearings • Business Equipment	• Consumer Applications • Gears • General Purpose	• Industrial Applications • Pulleys • Rollers
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.41	1.41 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ² (190°C/2.16 kg)	8.2 g/10 min	8.2 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.025 to 0.027 in/in	2.5 to 2.7 %	ASTM D955
Water Absorption (24 hr, 0.125 in (3.18 mm))	0.20 %	0.20 %	ASTM D570
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ³	365000 psi	2520 MPa	ASTM D638
Tensile Strength ³ (Yield)	9500 psi	65.5 MPa	ASTM D638
Tensile Elongation ³ (Break)	40 %	40 %	ASTM D638
Flexural Modulus	365000 psi	2520 MPa	ASTM D790
Flexural Strength	13000 psi	89.6 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	1.3 ft-lb/in	69 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	230 °F	110 °C	
CLTE - Flow	0.000048 in/in/°F	0.000086 cm/cm/°C	ASTM D696

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82.2 °C

Copyright ©, 2012 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	370 to 410 °F	188 to 210 °C
Mold Temperature	120 to 180 °F	48.9 to 82.2 °C

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

³ Type I, 0.20 in/min (5.1 mm/min)

CONTACT INFORMATION**Americas**

Mexico - Toluca
+52 722 2790200

United States - Avon Lake
+1 440 930 1000

Asia

China - Shanghai
+86 21 5080 1188

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Tianjin
+86 22 2532 8818

India - Navi Mumbai
+91 22 27784426/22781218

Japan - Tokyo
+81 369 129 102

Singapore - Singapore
+65 6861 9325

Taiwan - Yonghe City,
+886 9396 99740

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314

Turkey - Basaksehir-Istanbul-Türkiye
+90 212 549 2256



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
Please Call Assesse
Belgium Phone Number +32
83 660 211

Copyright ©, 2012 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.