



Therma-Tech™ NN-3000 TC Polyamide 66

Key Characteristics

Product Description	
Therma-Tech™ Thermal Management Compounds have been engineered to combine the heat transfer and cooling capabilities of metals with the design freedom, weight reduction and cost advantages of thermoplastics. These materials provide the benefits of proprietary conductive additive technologies and the performance of select engineering thermoplastic resins. Therma-Tech compounds have been shown to improve thermal conductivity up to 100-times that of conventional plastics and can be used in a wide range of thermal management applications.	
General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • North America • South America
Features	• Electrically Conductive • Thermally Conductive
Uses	• Automotive Applications • Consumer Applications • Housings • Automotive Under the Hood • Electrical/Electronic Applications • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.38	1.38 g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.0070 to 0.0080 in/in	0.70 to 0.80 %	ASTM D955
Water Absorption (24 hr, 0.125 in (3.18 mm))	0.60 %	0.60 %	ASTM D570
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	1.50E+6 psi	10300 MPa	ASTM D638
Tensile Strength ² (Yield)	11000 psi	75.8 MPa	ASTM D638
Tensile Elongation ² (Break)	0.70 %	0.70 %	ASTM D638
Flexural Modulus	1.34E+6 psi	9240 MPa	ASTM D790
Flexural Strength	12000 psi	82.7 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.250 in (6.35 mm), Injection Molded	0.80 ft-lb/in	43 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	480 °F	249 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	460 °F	238 °C	ASTM D648
Thermal Conductivity	24 Btu-in/hr/ft ² /°F	3.5 W/m/K	ASTM C177
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+5 to 1.0E+6 ohm	1.0E+5 to 1.0E+6 ohm	ASTM D257
Volume Resistivity	1.0E+6 to 1.0E+7 ohm-cm	1.0E+6 to 1.0E+7 ohm-cm	ASTM D257

Copyright © 2012 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	540 to 570 °F	282 to 299 °C
Mold Temperature	150 to 200 °F	65.6 to 93.3 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

CONTACT INFORMATION

Americas

Mexico - Toluca
+52 722 2790200

United States - Avon Lake
+1 440 930 1000

Asia

China - Shanghai
+86 21 5080 1188

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Tianjin
+86 22 2532 8818

India - Navi Mumbai
+91 22 27784426/22781218

Japan - Tokyo
+81 369 129 102

Singapore - Singapore
+65 6861 9325

Taiwan - Yonghe City,
+886 9396 99740

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastró (Huesca)
+34 974 310 314

Turkey - Basaksehir-Istanbul-Türkiye
+90 212 549 2256



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
Please Call Assesse
Belgium Phone Number +32
83 660 211

Copyright ©, 2012 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.