

**Product Description**

EL-Pro P700J is a homopolymer polypropylene resin suitable for general purpose product produced from injection molding process.

**Typical Application**

- Household product, Toy, Office accessory
- Food container, Infant article
- Fruit basket

**Product Characteristics**

- High processibility and odorless
- Good stiffness
- Food contact applicable (Complies with U.S FDA 21 CFR 177.1520)

**Physical Properties**

Property	Test Method	Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	12	g/10 min
Density	ASTM D 1505	0.910	g/cm <sup>3</sup>
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	320	kg/cm <sup>2</sup>
Tensile Strength at Break	ASTM D 638 @ Crosshead speed 50 mm/min	200	kg/cm <sup>2</sup>
Elongation at Break	ASTM D 638 @ Crosshead speed 50 mm/min	650	%
Flexural Modulus	ASTM D 790	14500	kg/cm <sup>2</sup>
Notched Izod Impact	ASTM D 256 @ 23°C	3	kg.cm/cm
Notched Izod Impact	ASTM D 256 @ 0°C	2	kg.cm/cm
Rockwell Hardness	ASTM D 785	90	R-Scale
Haze	ASTM D 1003	47	%
Gloss	ASTM D 2457	51	%
Melting Point	ASTM D 2117	163	°C
Vicat Softening Point	ASTM D 1525	155	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm <sup>2</sup>	110	°C
	ASTM D 648 @ 18.5 kg/cm <sup>2</sup>	65	°C
Brittleness Temperature	ASTM D 746	-20	°C
% Shrinkage (2mmt) MD	TPE Method	1.2	%
	TD	1.2	%
Flamability	UL - 94	HB	-

Note : Conversion factor for changing unit from kg/cm<sup>2</sup> to MPa is divided by 10.20

**Processing Techniques**

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 230-270°C	Mold temperature: 25-70°C	Injection speed: Fast	Screw speed 40-70 rpm
Pressure: Injection 40-80%,	Packing and Holding 30-60%,	Back 10%	of Max. Pressure

**Product Available Form**

- Pellet

**Product Handling**

- 25 kg loose bag
- Big Bag with specified weight

**Product Technical Assistance**

For technical assistance or further information on this product or any other EL-Pro products, please contact EL-Pro representatives.

The information presented in this data sheet is offered in good faith. SCG Plastics Co., Ltd. accepts no responsibility for the accuracy or interpretation of the information presented. The users have to establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all related laws.