

## TECHNYL® A 216 S30

Product Datasheet - November 2004

### Description

Polyamide 66, reinforced with 30% of glass spheres, for injection moulding.

### Product Applications

TECHNYL® A 216 S30 is used in all sectors of industry, offering an excellent combination between thermal and mechanical properties. This grade is recommended for mechanical components which require a very good surface finish with low warpage, and good compression strength.

This product is available in natural, black, grey, red, white, and in special colours on request

### Processing

The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content of less than 0,2% with a dehumidified air drying equipment at approx 80°C.

Recommended moulding conditions:

Barrel temperatures:

- feed zone 260 - 270°C
- compression zone 270 - 280°C
- front zone 280 - 290°C

Mould temperatures: 60 at 80°C

For more detailed information, please refer to the technical sheet Injection moulding.

### Safety

Please refer to the Safety Data Sheet Q1QIJEQN8FS

# TECHNYL® A 216 S30

The values of properties are for natural grade.

Properties	Standards	Unit	Values	
			d.a.m**	Cond.**
<b>Physical</b>				
Water absorption (24 h at 23°C)	ISO 62	%	0.75	-
Density	ISO 1183-A	g/cm3	1.37	-
Molding shrinkage Parallel (1) (RHODIA-EP)	RHODIA-EP	%	1.60	-
Molding shrinkage normal or perpendicular (1) (Rhodia EP)	RHODIA-EP	%	1.60	-
Molding Shrinkage Isotropy	RHODIA-EP		1	-
<b>Mechanical</b>				
Tensile modulus	ISO 527 type 1 A	MPa	4500	2500
Tensile strength at yield	ISO 527 type 1 A	MPa	80	-
Tensile strain at yield	ISO 527 type 1 A	%	4	-
Tensile strain at break	ISO 527 type 1 A	%	9	12
Tensile strength at break	ISO 527 type 1 A	MPa	80	60
Flexural modulus	ISO 178	MPa	3850	1900
Flexural maximum stress	ISO 178	MPa	135	65
Charpy notched impact strength	ISO 179/1eA	kJ/m2	3.5	5
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	20	NB
Izod notched impact strength	ISO 180/1A	kJ/m2	2.5	5
<b>Flamability</b>				
Flammability UL 94 (Thickness 1,6 mm)	ISO 1210/UL 94		HB	-
<b>Thermal</b>				
Melting Temperature	ISO 11357	°C	263	-
Heat deflection temperature, 1,8 Mpa	ISO 75/Af	°C	95	-
Coef. of Linear thermal expansion normal or perpendicular ( 23°C to 85°C)	ISO 11359	E-5 / °C	6	-
<b>Electrical</b>				
Dissipation factor	IEC 60250		0.02	0.11
Volume resistivity	IEC 60093	E14.Ohm.cm	5	1
Surface resistivity	IEC 60093	E14.Ohm	5	0.005000
Dielectric strength	IEC 60243	kV/mm	30	26
Comparative tracking index sol. A	IEC 60112	Volt	600	500

## Identification Code : >PA66-GB30<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a format commitment or warranty of our part. Compliance of our products with your conditions or use can only be determined pursuant to your own prior appropriate list. The listed values of properties are for natural grade, if not otherwise specified.

\* d.a.m = Dry As Moulded.

\*\* Cond. = Conditioned according ISO 1110.



Engineering Plastics

